



TECHNICAL SHEET



CC/1758

BARNIZ UHS 3:1 / 3:1 UHS CLEAR COAT

LOW VOC

DESCRIPTION

CC/1758 is a UHS clearcoat for the repair and refinish of OEM painted vehicles with clearcoat on a bicoat system. Optimized for its application on the **W6000 Series**, it stands out for its:

- Easy application.
- High yield.
- Excellent finish, with more than 100% gloss.
- Several drying options in combination with the hardeners and thinners.
- High surface hardness, high abrasion resistance to Car-Wash machines.
- High UV resistance.

PRETREATMENT/ CLEANING

Designed for application on the **W6000 Series** or on existing paint in good condition previous sanding.

The use of tack cloth is recommended.

Should only be painted when the bicoat base is completely matt, according to the recoating times indicated by the manufacturer.

CC/1758

BARNIZ UHS 3:1 / 3:1 UHS CLEAR COAT

APPLICATION

APPLICATION					
	Mixing ratio Volume	HA/8010 Slow HA/8020 Medium HA/8030 Fast HA/8040 Extra-Fast	>30°C 20-30°C 15-25°C 10-20°C	2h. 2h. 1h. 0,5h.	
	Application viscosity	18-20" S0/5020 0-5%			
	Gravity spraygun Application pressure	1,2 - 1,4 mm 2 - 2,5 bar			
	Nr of layers Thickness	1 light coat 1 full coat 50-60 µm			
	Thinner evaporation time	5-10' between layers 20' before heating			
	Drying time 20°C IR Middle wave 60°C	HA/8010 3-4h. 30' 35'	HA/8020 3-4h. 30' 35'	HA/8030 3h 20' 30'	HA/8040 2h 15' 20'

ATTENTION: In the case of flexible or semi-flexible plastic supports, it is possible to add 5% of SINNEK PL / 7078 additive on component A. The proportions of hardener and thinners remain the same.

FINISH

	Polish 20°C IR Middle wave 60°C	HA/8010	HA/8020	HA/8030	HA/8040
		Next day	Next day	8h	4h

Recoatable: within 24 hours.

CC/1758

BARNIZ UHS 3:1 / 3:1 UHS CLEARCOAT



SAFETY AND HYGIENE

Recommendable to use the appropriate personal protective equipment during application to avoid irritation of breathing tract, skin and eye irritation.

For professional use only.

STORAGE

Keep covered in a dry and ventilated place, avoiding direct exposure to sunlight. We advise Temperature above 5°C, recommended between 15-30°C.

VOC

CC / 1758 has a lower organic solvent content than the traditional, compliant with the European Norm 2004/42/EC II (D) (420) <420 g/l

The information contained in this Technical Data Sheet is based on our knowledge and experience and with it we try to advise and inform, being the responsibility of the user to take the necessary measures to guarantee the intended purpose of the product. FOR PROFESSIONAL USE EXCLUSIVELY.

SINNEK

Ugarte Industrialdea, 147
20720 Azkoitia (Gipuzkoa) - Spain

T: + 34 943 74 28 00
sinnek@sinnek.com
www.sinnek.com